

Foreverest Resources Ltd

对叔丁基苯酚甲醛树脂

FR2402

我司供应的FR2402树脂是100%脂溶性松香改性酚醛树脂。可作为天然橡胶、丁基橡胶和丁苯橡胶[SBR]的固化剂，其中尤其适合用于固化丁基橡胶。

Substance Identification

Synonyms	松香改性酚醛树脂
CAS	N/A
EINECS	N/A
FEMA	N/A

HS.CODE	N/A
Molecular Formula	N/A
Moleclar Weight	N/A

Application & Uses

- 氯丁橡胶胶黏剂原料，其制成的胶黏剂可应用于鞋底粘合
- 外部表面涂层原料，如船体涂料、地板漆、水性印刷油墨、防锈漆等
- 涤纶胶带、油管防腐胶黏剂或其它类型工业级胶黏剂的增粘剂、增强剂和硫化剂

Features & Benefits

- 可改善胶黏剂粘性
- 稳定性强
- 较大的延伸强度，且不易变形
- 溶于芳烃，烷烃，卤代烃，酯，酮，桐油等

Sales Specification

ITEM	VALUE
灰分含量（%）	0.3% max
游离酚含量	1% max
脂溶性（与桐油1:2在240℃条件下）	完全溶解
羟甲基含量	9~15%
软化点□R&B□	82~120℃
水含量	1% max

Similar Specs

- Rosin Modified Phenolic Resin
- Rosin Modified Phenolic Resin
- Rosin Modified Phenolic Resin

Package

- 纤维复合纸板桶，25公斤
- 纤维复合纸板桶，250公斤

GHS Hazard Statements

Storage

- 避免光线直照
- 和氧化物隔离贮存
- 贮存和运输方式须符合当地法律法规要求
- 贮存在阴凉、干燥处
- 密封贮存

Relation Products

- [Alkyl Phenolic Resin](#)
- [Reactive Alkyl Phenolic Resin](#)
- [Terpene Phenolic Resin](#)

Remark

The above information is believed to be accurate and presents the best explanation currently available to us. We assume no liability resulting from above content. The technical standards are formulated and revised by customers' requirement and us, if there are any changes, the latest specification will be executed and confirmed in the contract.

Manage consent