

# Foreverest Resources Ltd

## 松香改性季戊四醇酯

P110255

松香改性季戊四醇酯是由改性松香与季戊四醇酯化制成，较之松香季戊四醇酯具有更高的软化点。其良好的耐水性、耐久性和亮度适合应用于工业级胶黏剂、涂料、油墨、模板和微电子等领域。

### Substance Identification

Synonyms	Pentaerythritol Ester of Polymerized Rosin   Penta Rosinate
CAS	N/A
EINECS	232-479-9
FEMA	N/A

HS.CODE	3806 9000
---------	-----------

Molecular Formula	C25H34O2
-------------------	----------

Molecular Weight	366.53626
------------------	-----------

---

## Application & Uses

- 与植物油聚合后应用于树脂胶、酚醛树脂涂料
- 应用于工业级热熔胶、压敏胶等各类胶黏剂
- 其它工业领域应用，如油墨、微电子、蜡纸等

## Features & Benefits

- 色彩清淡
- 耐高温
- 耐水性
- 耐黄变
- 粘性高
- 不溶于醇溶剂
- 可与植物油良好溶合
- 部分溶于石油制品
- 溶于焦油
- 溶于松节油等类似溶剂

## Sales Specification

ITEM	VALUE
酸值□mgKOH/g□	≤25
颜色□Fe-Co□	≤3~5
软化点□R&B□°C□	110~120
溶解度（与苯1:1）	完全溶解于苯乙醇、酒精和甲苯混合物

## Similar Specs

[Pentaerythrite Modified Rosinate](#)

[Pentaerythrite Modified Rosinate](#)

[Pentaerythrite Modified Rosinate](#)

## Package

- 塑料复合纸袋，25公斤，内含PE内膜

# GHS Hazard Statements

## Storage

- 贮存于阴凉、干燥地方
- 与氧化物隔离贮存
- 运输过程中注意防止氧化
- 密封贮存
- 远离火苗、明火及火源

## Relation Products

- [Colorless Pentaerythritol Hydrogenated Rosinate](#)
- [Pentaerythritol Ester of Maleic Rosin](#)
- [Pentaerythritol Hydrogenated Rosinate](#)
- [Pentaerythrityl Rosinate](#)

## Relation Articles

- [Progress on the patents about the modifications of gum rosin and their applications](#)
- [Choosing the Correct Soldering Flux Types and Their Advantages/Disadvantages](#)

- [Role of Resin in Printing Ink](#)

## Remark

### — DISCLAIMER —

The above information is believed to be accurate and represents the best explanation currently available to us. However, no liability is assumed for any consequences arising from the use of this content. The technical standards for our products are developed and updated jointly by our customers and ourselves; where any changes occur, the latest specification shall prevail and will be confirmed in the relevant contract. All suggestions and data provided are based on information we consider to be reliable and are offered in good faith, but without any guarantee, as the conditions and methods of use of our products are beyond our control. Foreverest® makes no warranties, whether express or implied, regarding the accuracy, completeness or suitability of this information, and expressly disclaims any implied warranty of fitness for a particular purpose. Prospective users should conduct their own tests and evaluations to determine the suitability of Foreverest® materials and any recommendations for their intended applications before adoption, and, where appropriate, should obtain confirmation or approval from the relevant regulatory authorities. Any references in this page to patents or patented technologies, including descriptive material derived from patents or citations of specific patent numbers, are provided for information only. They must not be interpreted as a recommendation to use our products in a manner that could infringe any third-party patent, nor as a grant of any licence or permission to use patents owned by Foreverest®.