Foreverest Resources Ltd

无色全氢化松香

400

Foreverest™ 无色全氢化松香400由氢化松香去除杂质后精制而得,纯粹无色。可用作各类固体、液体助焊剂原料,胶黏剂原料和用于深加工浅色系树脂。本产品可替代 Eastman® 产品□

Substance Identification

Synonyms

CAS N/A

EINECS 266-041-3

FEMA	N/A
HS.CODE	38069000
Molecular Formula	N/A
Moleclar Weight	N/A

Application & Uses

- 1. 固体/液体助焊剂原料
- 2. 热熔型胶黏剂原料
- 3. 浅色系合成树脂原料

Features & Benefits

Sales Specification

ITEM	VALUE
外观	白色透明固体
颜色(哈森,#)	50~100

ITEM	VALUE
软化点□R&B, °C□	74~78
四氢树脂酸(%)	40~60
氢化树脂酸(%)	≥92
脱氢枞酸(%)	≤10
酸值[]mgKOH/g[]	167~168
灰分含量(%)	≤0.008
不皂化物含量(%)	≤5.0
枞酸 (%)	≤0.5

Package

- 铁桶, 225公斤
- 塑料复合纸袋, 25公斤

GHS Hazard Statements

Storage

- 避免光线直照
- 和氧化物隔离贮存
- 贮存和运输方式须符合当地法律法规要求
- 贮存在阴凉、干燥处
- 密封贮存

Relation Products

- Colorless Glyceryl Hydrogenated Rosinate
- Colorless Pentaerythritol Hydrogenated Rosinate
- Hydrogenated Rosin

Relation Articles

- Methyl Hydrogenated Rosinate for Personal Care and Cosmetics
- Application of Gum Rosin
- Frequently asked questions about new transparent tackifiers Hydrogenated terpene/polyterpene resins
- How to choose tackifier resins for Non-woven adhesives
- Choosing the Correct Soldering Flux Types and Their Advantages/Disadvantages

Remark

The above information is believed to be accurate and presents the best explanation currently available to us. We assume no liability resulting from above content. The technical standards are formulated and revised by customers' requirement and us, if there are any changes, the latest specification will be executed and confirmed in the contract.

Manage consent