# Foreverest Resources Ltd

# 无色氢化松香季戊四醇酯

#### PEHR100E

无色氢化松香季戊四醇酯PEHR100E以松香酯为原料,与季戊四醇酯化后经催化加氢等一系列技术单元合成而制得的多元醇超浅色增粘树脂。具有颜色超浅、气味极低、耐热性、耐候性优秀等特点,主要应用于显示屏保护膜、药用贴剂、卫生制品等黏合剂、压敏胶、热熔胶。

#### Substance Identification

Synonyms Colorless Pentaerythritol Ester of Hydrogenated Rosin | CPEHR

CAS N/A

EINECS 264-848-5

FEMA N/A

HS.CODE	38069000
Molecular Formula	N/A
Moleclar Weight	N/A

## Application & Uses

- 显示屏保护膜用增粘树脂
- 药用贴剂用增粘树脂
- 卫生制品等增粘树脂
- 压敏胶、热熔胶用增粘树脂

#### Features & Benefits

- 颜色超浅
- 气味极低
- 优异耐热性
- 优异耐候性

### Sales Specification

ITEM	VALUE
溶解度(与甲苯1:1)	清
颜色[]Hazen Unit[]	≤150
酸值□mg/g□	20~30
软化点□R&B, °C□	95~105
碘值□ gl2/100g□	≤15

## Similar Specs

Colorless Pentaerythritol Hydrogenated Rosinate

Pentaerythritol Hydrogenated Rosinate

Pentaerythritol Hydrogenated Rosinate

# Package

- 桶装, 225公斤
- 塑料复合纸袋, 25公斤

#### **GHS Hazard Statements**

### Storage

- 避免光线直照
- 和氧化物隔离贮存
- 贮存和运输方式须符合当地法律法规要求
- 贮存在阴凉、干燥处
- 密封贮存

#### **Relation Products**

- Colorless Fully Hydrogenated Rosin
- Colorless Glyceryl Hydrogenated Rosinate
- Pentaerythritol Ester of Maleic Rosin
- Pentaerythritol Hydrogenated Rosinate

#### **Relation Articles**

- How to choose tackifier resins for Non-woven adhesives
- Choosing the Correct Soldering Flux Types and Their Advantages/Disadvantages

### Remark

The above information is believed to be accurate and presents the best explanation currently available to us. We assume no liability resulting from above content. The technical standards are formulated and revised by customers' requirement and us, if there are any changes, the latest specification will be executed and confirmed in the contract.

Manage consent