

# Foreverest Resources Ltd

## 丁苯橡胶（食品级）

SSBR1027

Foreverest™ SSBR1027食品级丁苯橡胶由溶聚法生产，具有色泽白、纯度高、无残留异味、耐低温性好等特点。是固特异食品级胶基PLIOGUM® 1027的优秀等同物。

*NOTE: PLIOGUM is the trademark of Goodyear*

## Substance Identification

Synonyms

溶聚丁苯橡胶 | Solution Polymerized Butadiene Styrene Rubber

CAS

N/A

EINECS

618-370-2

FEMA	N/A
HS.CODE	N/A
Molecular Formula	(C8-H8.C4-H6)x-
Moleclar Weight	N/A

---

## Application & Uses

- 口香糖胶基
- 泡泡堂胶基
- 食品生产领域

## Sales Specification

ITEM	VALUE	TEST METHOD & UNIT
外观	白色或浅黄色固体	
1,3-丁二烯含量	0.5 max	mg/kg
砷含量	3.0 max	mg/kg
灰分含量	0.5 max	mg/kg
二丁基羟基甲苯含量	2500 to 5000	mg/kg

ITEM	VALUE	TEST METHOD & UNIT
镉含量	1.0 max	mg/kg
铅含量	3.0 max	mg/kg
锂含量	75 max	mg/kg
汞含量	3.0 max	mg/kg
醌含量	20 max	mg/kg
正己烷残留物含量	100 max	mg/kg
苯乙烯残留物含量	20 max	mg/kg
挥发性物质含量	0.7 max	mg/kg
苯乙烯键合含量	22.0 to 26.0	%
门尼粘度	55 to 67	ML(1+4), @100°C, MU

ITEM	VALUE	TEST METHOD & UNIT
外观	白色或浅黄色固体	
1,3-丁二烯含量	0.5 max	mg/kg
砷含量	3.0 max	mg/kg
灰分含量	0.5 max	mg/kg
二丁基羟基甲苯含量	2500 to 5000	mg/kg

ITEM	VALUE	TEST METHOD & UNIT
镉含量	1.0 max	mg/kg
铅含量	3.0 max	mg/kg
锂含量	75 max	mg/kg
汞含量	3.0 max	mg/kg
醌含量	20 max	mg/kg
正己烷残留物含量	100 max	mg/kg
苯乙烯残留物含量	30.0 max	mg/kg
挥发性物质含量	1.0 max	mg/kg
苯乙烯键合含量	45.0 to 50.0	%
门尼粘度	66 to 78	ML(1+4), @100°C, MU

## Package

- 硬纸板箱，900公斤每托，11箱（托）每20尺柜
- 复合纸袋，25公斤，640包（约1.6吨，带20个托盘）每20尺柜
- 复合纸袋，25公斤，900包（约2.25吨，无托盘）每20尺柜

# GHS Hazard Statements

此产品在暂无可用数据，[点击查看UNECE对GHS的统一分类和标签管理制度](#)

## Storage

- 密封贮存于通风、干燥、阴凉处
- 和氧化物隔离贮存
- 禁止内服食用

## Relation Products

- [Chewing Gum Base](#)
- [Glyceryl Monostearate](#)
- [Glyceryl Monostearate](#)
- [Polyvinyl Acetate](#)
- [Polyvinyl Acetate](#)
- [Polyvinyl Acetate](#)

## Remark

*The above information is believed to be accurate and presents the best explanation currently available to us. We assume no liability resulting from above*

*content. The technical standards are formulated and revised by customers' requirement and us, if there are any changes, the latest specification will be executed and confirmed in the contract.*

Manage consent