

Foreverest Resources Ltd

Wood Based Activated Carbon (Sugar Uses)

WFA

WFA is wood based activated carbon used for sugar decolorization process. It also can be used for refining process of saccharin, glucose, xylitol.

Substance Identification

Synonyms

CAS

N/A

EINECS

231-153-3

FEMA

N/A

HS.CODE	380210
Molecular Formula	C
Molecular Weight	12.01

Application & Uses

- Sugar Refining Process

Sales Specification

ITEM	VALUE
Adsorption of Methylene Blue, ml/0.1g	13 to 17 min
Adsorption of Caramel, %	100 to 120 min
LOD Value, %	10 max
PH Value	3 to 5
Content of Ash, %	5 max
Content of Iron,%	0.05 max
Content of Chlorine, %	0.08 max

ITEM	VALUE
Particle Size, 200 mesh, %	90 min

Package

- Plastic bag with inner film, 20kg net each

GHS Hazard Statements

There is currently no available data for this product, click to view [GHS Classification and Labelling by UNECE](#).

Storage

- Keep away from heat, sparks and open flame. Guard against dust accumulation of this material
- Keep containers closed when not in use. Store at ambient temperature and atmospheric pressure
- Keep container tightly closed. Keep out of the reach of children

Relation Products

- [Wood Based Activated Carbon \(Amino Acid Uses\)](#)
- [Wood Based Activated Carbon \(Food Uses\)](#)
- [Wood Based Activated Carbon \(Medical Uses\)](#)
- [Wood Based Activated Carbon \(Water Treatment Uses\)](#)

Remark

— DISCLAIMER —

The above information is believed to be accurate and represents the best explanation currently available to us. However, no liability is assumed for any consequences arising from the use of this content. The technical standards for our products are developed and updated jointly by our customers and ourselves; where any changes occur, the latest specification shall prevail and will be confirmed in the relevant contract. All suggestions and data provided are based on information we consider to be reliable and are offered in good faith, but without any guarantee, as the conditions and methods of use of our products are beyond our control. Foreverest® makes no warranties, whether express or implied, regarding the accuracy, completeness or suitability of this information, and expressly disclaims any implied warranty of fitness for a particular purpose. Prospective users should conduct their own tests and evaluations to determine the suitability of Foreverest® materials and any recommendations for their intended applications before adoption, and, where appropriate, should obtain confirmation or approval from the relevant regulatory authorities. Any references in this page to patents or patented technologies, including descriptive material derived from patents or citations of specific patent numbers, are provided for information only. They must not be interpreted as a recommendation to use our products in a manner that could infringe any third-party patent, nor as a grant of any licence or permission to use patents owned by Foreverest®.